

**NAME: PGPOQ7I2**

**PRODUCT DATA SHEET**

Analysis	Test method	Condition	Unit	Value
MFI (300 C)	ASTM D1238	1.2 Kg load	g/10 min	7.1-12
Density	ASTM D792	25 C	g/cm3	1.2
Tensile Strength	ASTM D638	@ yield	Mpa	>60
Modulus of Elasticity	ASTM D638	--	Mpa.	2000-2400
Elongation	ASTM D638	@ Break	%	>90
Dielectric Strength	ASTM D149	@50 Hz	Kv/mra	>20
Oharpy Impact Strcugth	ASTM D6110	Notched	Kj/rn2	>25
Vicat soft. Temp.	ASTM D1525	50 N, 50C/h	C	142-146
Transinitflnce	ASTM D1003	Thickness 2mm	%	Sr80
Solvent Content	GC (int-st)	-	ppm	Max. 3000