

NAME: LL22402(Basell Grade: 22402) **With UV****Typical data: (Table)**

Typical properties	Method	Unit	Value
MFI@190°C, 2.16 kg	ISO 1133	gr/10min	1.8 - 2.1
Density	ISO 1183	gr/ml	0.920 - 0.923
Tensile STR.@ Yield	ASTM D882-10	Mpa	18 - 21
Tensile STR.@ Break	ASTM D882-10	Mpa	54 - 36
Elong.@ Break	ASTM D882-10	%	780 - 990
Elmendorf Tear Strength	ASTM D1922-09	g/ 25 Jim	35 - 325

Main application & Characteristics:**“Typical applications are:**

for use in lean and rich blend blown film application such as overwrap, Counter bags, shrink film and boil in the bag applications. Artificial grass